

Properties	Test Method as per EN - 438-2 CLAUSE NO.	Property or Attribute	Unit (Max. or Min.)	Value as per EN - 438-2	Airolam Values
Thickness Maximum Variation	5		mm	±0.10mm	±0.10mm
Length & Width	6		mm	+10mm -0.0mm	+10mm -0.0mm
Density	EN ISO 1183	Density	g/cm ³	≥1.35	>1.35
Resistance to Surface wear	10	Wear Resistance	Revolution (min)	≥350	>400
Resistance to Impact by Small diameter Ball	20	Spring Force	N(min)	≥20	>20
Resistance to Scratching	25	Force	Rating (see annex a)	3	≥3
Dimensional stability at elevated temperature	17	Cumulative dimensional change	% long % Cross	≤ 0.55 ≤ 1.05	<0.45 < 0.90
Resistance to immersion in boiling water	12	Appearance	Grade (min) Gloss Finish Other finishes	3 4	>3 >4
Resistance to dry Heat at 180°C	16	Appearance	Grade (min) Gloss Finish Other finishes	3 4	>3 >4
Resistance to Staining	26	Appearance	Rating Group-1&2 Group-3	≥5 ≥4	5 ≥4
Resistance to water vapor	14	Appearance	Grade (min) Gloss Finish Other finishes	3 4	>3 >4
Light Fastness (Xenon arc)	27	Contrast	Gray Scale Rating	4 to 5	>4
Resistance to cigarette burn	30	Appearance	Grade (min)	3	>3
Resistance to Cracking under stress	23	Appearance	Grade (min)	4	>4